



# KM Sealed Edge Polyester Wipers

## WW-3009 (9" x 9")

### **Specification**

Performance Characteristics	Test Method	Results
		WW3009
Basis weight (g/m <sup>2</sup> )	ASTM D3776	150
Absorbency		
Capacity (ml/m <sup>2</sup> )	IES-RP-CC004.2	400
Efficiency (ml/g)		2,67
Time to sorption (sec.)		2
Tensile strength (kg)	ASTM D5034	
Machine direction (MD)		70,7
Cross direction (XD)		66,5
Thickness (μm)		570
<b>Contamination Characteristics</b>		
Particle (>0.5μm)		
Orbital shake, SEM (ea/m <sup>2</sup> , >0.5μm)	IES-RP-CC004.2	24x10 <sup>6</sup>
Dry flex (ea/cft, >0.5μm)		50
NVR (g/m <sup>2</sup> ).	IES-RP-CC004.2	
DI water		0,02
IPA		0,1
Extractable Ions(ppm)	IES-RP-CC004.2	
Na		0,2
K		0,01
Cl		0,3
NO <sub>2</sub>		0,01